

# HYTEX R15 SDC

Cotton / Canvas Dry Chemical Dyeing, Rot & Waterproof



Red



Orange



Green



Blue



White

Weight:	14 oz / 474 gsm (+/- 5)	
Width:	91 cm	BS2286
Roll length:	approx. 100 m	

PHYSICAL PROPERTY	SPEC.	TOL	TEST METHOD
Bath test- leakage (mls)	Nil	-	Internal
Bath test- Absorbtion (%)	16 max	-	Internal
Crushed cone test- leakage (mls)	Nil	-	BS 3408: 1992
Cone test- Absorbtion (%)	Nil	-	"
Hydrostatic head tested (10cm / min)	18		ISO 811
Colour fastness / dry rub	3	-	ISO 105 X 12 BS 1006 X 12
Colour fastness / wet rub	3	-	"
Rotproof content	Pass	-	BS 2087 PT2- 6.5 METH. 5
Spray rating	3		ISO 4920 BS EN24920
Tensile Strength, Warp (N)	1000	-	EN ISO 13934-1
Tensile Strength, Weft (N)	900	-	"
Wing Rip Tear, Warp (N)	35	-	EN ISO 13937-1
Wing Rip Tear, Weft (N)	30	-	"

tel. 0141 773 5469

fax. 0141 773 5455

email. info@mitco.co.uk

[www.mitco.co.uk](http://www.mitco.co.uk)