

# Mitco Webtex 16

Polyester Cotton Ripstop, Rot & Waterproof



Red



Yellow



Green



Blue

Weight:	580 / m2	+/- 50
Width:	91 cm	-
Roll length:	100 m	

PHYSICAL PROPERTY	SPEC.	TOL	TEST METHOD
Bath test- leakage (mls)	Nil	-	Internal
Bath test- Absorbtion (%)	16	Max	Internal
Crushed cone test- leakage (mls)	Nil	-	Def Stan 83-27
Cone test- Absorbtion (%)	Nil	-	Def Stan 83-27
Hydrostatic Test (10cm/min)	35	-	ISO 811
Colour fastness / dry rub	3	-	ISO 105 x 12      BS 1006 x 12
Colour fastness / wet rub	3	-	ISO 105 x 12      BS 1006 x 12
Rotproof content (%)	Pass	-	BS 2087 PT2-6.5 Meth 5
Spray rating	2	-	ISO 4920      BS EN 24920
Tensile Strength, Warp (N)	2500	-	EN ISO 13934-1
Tensile Strength, Weft (N)	1650	-	EN ISO 13934-1
Wing Rip Tear, Warp (N)	200	-	BS EN ISO 13937-3
Wing Rip Tear, Weft (N)	200	-	BS EN ISO 13937-3

tel. 0141 773 5469

fax. 0141 773 5455

email. info@mitco.co.uk

[www.mitco.co.uk](http://www.mitco.co.uk)